

months.

Safetv

the material.



# **KÖSTER Swellable Grout**

Technical Data Sheet SL 252 025

bags can be stored for a period of 6 months and plastic bags for 12

Contains Portland cement. Reacts caustic. Thus protect skin and eyes

from contact. In case of contact, rinse thoroughly with water. Observe all governmental, state, and local safety regulations when processing

Issued: 2021-06-30

# Swellable self-leveling grout

## Features

KÖSTER Swellable Grout is a fine-grained, normal setting grout mortar, formulated with a moderately expanding component. It provides a good flow spread, is pourable, and has a pot life of at least 45 mins. KÖSTER Swellable Grout is resistant to de-icing and other harmful salts as well as oils and lubricants.

# **Technical Data**

Mixing water Color Density Density of freeh merter	3.5 Liter cement gray 1.9 kg / I
Density of fresh mortar	approx. 2.10 kg / I (incl. mixing water)
Largest grain size	approx. 1.5 mm
Begin of setting time	after approx. 90 Min (+20°C)
Maximum thickness	25 cm
Compressive strength 1 Day	> 20 N / mm²
Compressive strength 7 Days	> 35 N / mm²
Compressive strength 28 Days	> 50 N / mm²
Fleural Tensile Strength 1 Day	> 4 N / mm <sup>2</sup>
Fleural Tensile Strength 28 Days	> 9 N / mm²
Trafficable at > $+10 \degree C$	after aprox. 18 hours
Swelling	approx. 0,4 %

# **Fields of Application**

KÖSTER Swellable Grout is suitable for pouring and filling i.e. void and concrete breakouts, for underpinning machine foundations, shelf rack columns, and as pocketing grout for installations and anchoring holes.

# Substrate

The substrate must be clean, solid, and stable. Remove all laitance and bond inhibiting soilings such as dirt and dust. It is recommended to prepare the substrate by high pressure water jetting. Pre-wet the substrate before installation. Remove any standing water.

# Application

KÖSTER Swellable Grout is slowly added to 3.5 liters of clean mixing water while constantly mixing using a slow rotating stirring device (recommended: KÖSTER Double Paddle Mixer, max. 400 rpm). Mixing time is a minimuam of 3 minutes. The grouting procedure should be carried out in one work step.

The material can also be pumped with all screw pumps from b&m, especially the BMP 7 (max. 10 m 3/4" hose, 1st gear, 10% speed).

### Consumption

1.9 kg / l void

#### Cleaning

Clean tools immediately after use with clean water.

# Packaging

SL 252 025

25 kg bag

### Storage

Store the material in a dry environment in originally sealed bags. Paper

The information contained in this technical data sheet is based on the results of our research and on our practical experience in the field. All given test data are average values which have been obtained under defined conditions. The proper and thereby effective and successful application of our products is not subject to our control. The installer is responsible for the correct application under consideration of the specific conditions of the construction process. This may require adjustments to the recommendations given here for standard cases. Specifications made by our employees or representatives which exceed the specifications contained in this technical guideline require written confirmation. The valid standards for testing and installation, technical guidelines, and acknowledged rules of technology have to be adhered to at all times. The warranty can and is therefore only applied to the quality of our products within the scope of our terms and conditions, not however, for their effective and successful application. This guideline has been technically revised; all previous versions are invalid.

KÖSTER BAUCHEMIE AG • Dieselstraße 1-10 • D-26607 Aurich • Tel. 04941/9709-0 • Fax -40 • info@koester.eu • www.koester.eu